



Sanitized® COLORGROUT

Cementitious Tile Grout 1-6 mm wide

DESCRIPTION

Sanitized COLORGROUT is a cementitious grout designed for use with most types of ceramic tiles and natural stone applications. The grout also contains a biocide, which provides it with a resistance to a broad spectrum of moulds and bacteria.

USES

- *Sanitized* COLORGROUT can be used in grout joints that are between 1 - 6 mm wide.
- *Sanitized* COLORGROUT can be used on internal or external wall and floor grouting applications.
- *Sanitized* COLORGROUT can also be used in swimming pools and wet areas.

SURFACE PREPARATION

- Before commencing grouting, ensure the tile adhesive has set firmly. This usually requires 24 hours with the majority of tile adhesives.
- Remove any spacer lugs, rake-out any excess adhesive and any loose or foreign material from the grout joints.
- In general, ensure the grout joints are clean and dry

MIXING

- Add clean water to a bucket, then slowly add the *Sanitized* COLORGROUT lump-free consistency is achieved.
- The mixing ratio is 20 kg powder to 4 - 4.5 lt of water.
- Allow the mix to stand for 10 minutes, re-stir then use the grout.
- When grouting swimming pools or over timber floors and substrates where movement is expected or for superior performance in general applications, use Davco GROUT-CURE Grout Additive or Davelastic instead of water

APPLICATION

- Prior to routing it is advisable to lightly dampen the grout joints, particularly with porous tiles or in hot conditions.
- Using a rubber float or squeegee work the grout into the joints in a diagonal motion making sure that the grout does not just sit on top of the joint i.e. the grout does not bridge the joint.
- Remove excess grout from the surface of the tiles with the rubber float or squeegee using a diagonal motion.
- Use a damp sponge to clean up the remainder of the grout. Regularly rinsing the sponge out to assist in cleaning.
- Finally remove any excess moisture from the grout joints, to avoid discolouration or colour variation problems.
- Allow the grout to cure for 24 hours before cleaning the grout haze with a soft dry cloth.

PRECAUTIONS

- Do not apply *Sanitized* COLORGROUT in temperatures above 40°C or below 5°C.
- *Sanitized* COLORGROUT is not suitable for use in harsh and demanding environments or where there are hygienic requirements i.e. commercial kitchens, public toilets, food processing plants etc. Use Davco Epoxy Grout for these types of installations.
- Cleaning or discolouration problems can occur with either textured, porous or natural stone tiles.
- Due to *Sanitized* COLORGROUT containing sand, scratching may occur with polished or soft glazed tiles.
- Do not apply *Sanitized* COLORGROUT in movement joints, use Lanko 612 ACRYLIQUE.
- Do not apply neat or strong acids on *Sanitized* COLORGROUT.
- For other uses or the use of *Sanitized* COLORGROUT in situations not mentioned in these instructions, contact your Davco Construction Materials state office

Sanitized COLORGROUT

Cementitious Tile Grout

1-6 mm wide

- Being cement based, *Sanitized* COLORGROUT is alkali in nature, which can cause dermatitis. Thus when using *Sanitized* COLORGROUT it is recommended that applicators must wear PVC or similar gloves and safety goggles.
- For a full MSDS on this product, contact your Davco Construction Materials state office.

COVERAGE

The coverage of the grout will vary depending upon the texture, size and thickness of the tile and the width of the grout joint.

Use the table below as a general guide:

Tile Size (mm)	Quantity of Grout Required kg/m ²			
	Joint Width (mm)			
	1.5	3	6	10
50 x 50 x 6	0.8	1.6	---	---
100 x 100 x 6	0.4	0.8	1.6	---
150 x 150 x 6	0.3	0.6	1.2	---
200 x 100 x 6	0.3	0.6	1.2	---
300 x 300 x 10	0.3	0.5	1.0	---

CLEAN UP

Tools and other equipment can be cleaned up with water while grout is still wet.

PACKAGING

Sanitized COLORGROUT is available in :

- 5 kg bags.
- 20 kg bags.

SHELF LIFE

Sanitized COLORGROUT has a shelf life of up to 12 months in unopened bags stored in a cool, dry elevated place.

TECHNICAL DATA

Properties :

- Appearance : Grey, White Powder
- Bulk Density : ~1.4 kg/litre
- Pot Life at 20°C : 40 minutes
- Drying Time at 20°C : 24 hours

DISCLAIMER

The use of this product is beyond the manufacturer's control, and liability is restricted to the replacement of material proven faulty. The manufacturer is not responsible for any loss or damage arising from incorrect usage. All workmanship must be carried out in accordance with AS 3958.1-1991.

The information contained herein is to the best of our knowledge true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of the product for a particular application. Users are asked to check that the literature in their possession is the latest issue.

Davco

Davco Construction Materials (Thailand) Co., Ltd.
 3rd Floor Lumpini II Building 247 Sarasin Road,
 Lumpini, Pathumwan, Bangkok 10330
 Telephone : 66 (0) 2651-9838 Facsimile : 66(0) 2651-8003
 E-mail : thaicustomerservice@davco.co.th
 Website : www.davco.co.th