

LANKO



CHARACTERISTICS

- **Creates a bonding key.**
- **Improves the bonding strength.**
- **Reduces the bubble effect.**
- **Easy to use.**

COVERAGE

- Approx. 40-60 cc/m² (before dilution).

PACKAGING

- 5 litre container.
- 20 litre container.

STORAGE

1 year from date of manufacture if stored in unopened original packing in dry, frost-free conditions.

DESCRIPTION

162 FLOW PRIME is a bonding primer which creates a bonding key on smooth and sealed substrates or porous substrates. It improves the condition of the surface, the bonding strength of the mortar and reduces the bubble effect (pin hole), absorption capacity of the substrate.

USES

Cementitious surfaces.

SPECIFICATIONS

- Appearance : White liquid
- Density : 1.1
- pH : 8-9
- Dry content : 50% approx.

WORK INSTRUCTIONS

Substrate preparation

- Substrates must be compliant with building regulations in force and at least 28 days old.
- Substrates must be clean, sound, solid, dust-free and without any traces of oil, laitance, curing compound, cracks, plaster or paint and any other product which may affect bonding.
- Scrape, brush off or vacuum clean all traces of plaster, laitance, paint, non-bonded adhesive.
- Substrates bearing excessive traces of wax, grease or paint must be stripped.
- All substrates must be thoroughly dusted.

Product preparation

- Mix 1 part of 162 FLOW PRIME with 3 parts of clean water until obtaining a homogeneous liquid.

Application

- Apply a regular coat of the product by brush or roller.
- Drying time : 2-4 hours depending on substrate, temperature and relative humidity.
- 162 FLOW PRIME can be covered as soon as it is touch-dry.
- The primer must be covered within 24 hours.

PRECAUTIONS

- Temperature range for use : 5°C - 30°C.
- Clean tools and equipments with water before the product dries.

LANKO
infotech

www.lanko.com.au
www.parexlanko.com

The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document.

Technical Documentation English-Version Aug 2006

Davco Construction Materials (Thailand) Co., Ltd.

3rd Floor Lumpini II Building 247 Sarasin Road, Lumpini, Pathumwam, Bangkok 10330 Telephone: 66(0)2651 9027-36 Facsimile: 66(0)2651 8003
e-mail : thaicustomerservice@davco.co.th, Overseas Offices : Australia (Sydney - Head Office), Singapore

LANKO

PAREXGROUP