

**OIL AND WATER REPELLENT  
PROVIDES LONG-LASTING PROTECTION  
AGAINST WATER, OIL AND GREASE**

**235**  
**LANKOPROTEC**

S U R F A C E P R O T E C T I O N

**LANKO**



### CHARACTERISTICS

- Provides long-lasting protection against water, oil and grease.
- Easy application.
- Does not modify the surface.
- Dirtproof, stainproof, non-adherent.
- Solvent and silicone free.
- Limits the development of micro-organisms.

### COVERAGE

0.04-0.7 litre/m<sup>2</sup> approx. depending on substrate porosity, i.e. : For 1 L of 235 LANKOPROTEC :

- Granite 25 m<sup>2</sup>
- Earthenware 21 m<sup>2</sup>
- Interlocking paving 8.5 m<sup>2</sup>
- Cement slabs 13 m<sup>2</sup>
- Marble 12 m<sup>2</sup>
- Terra cotta 8 m<sup>2</sup>
- Concrete 6 m<sup>2</sup>
- Cement coating 3.5 m<sup>2</sup>
- Freestone 1.4 m<sup>2</sup>

(Average values provided as an example)

### PACKAGING

- 1 litre container
- 5 litre container

### STORAGE

2 years from date of manufacture if stored in unopened original packing in cool, dry, frost-free conditions.

### DESCRIPTION

235 LANKOPROTEC is a powerful waterproofing and oilproofing agent. Provides long-lasting protection of horizontal and vertical surfaces against water, oil, grease and pollution.

235 LANKOPROTEC does not modify the initial appearance of the substrate and does not affect gas and steam permeability. By providing such protection, 235 LANKOPROTEC facilitates the removal of graffiti and other general stains. It remains effective after several washing cycles and is UV-resistant. Being non-adherent, it is easy to remove chewing gum and prevents the build-up of micro-organisms on treated surfaces. Presented in the form of an aqueous emulsion, 235 LANKOPROTEC is non-toxic and environmentfriendly.

### USES

235 LANKOPROTEC is particularly well-suited for the treatment of porous substrates such as :

- Slabs and paving stones.
- Roof-tiles, brickwork, terracotta tiles.
- Natural or reconstituted stone, marble, earthenware.
- Joints between stone, brickwork, tiles.
- Concrete, deactivated and architectural concrete (urban furniture).
- Mortar, facade coatings, Monuments, Plaster.

### SPECIFICATIONS

- Appearance : Amber liquid.
- Density at 20°C : 1
- pH : 4.5

### WORK INSTRUCTIONS

#### Substrate preparation

- The substrate must be clean, sound, dust-free, and dry or slightly damp prior to application. (leave for 3 days after high pressure cleaning and 24 hours after rain).
- For fresh or deactivated concrete, allow a minimum of 7 days curing (dependent on climatic conditions).
- Remove any traces of efflorescence, moss and mould.

#### Application

- Apply with a brush, roller or spraying machine, inside or outside.
- Optimum results are obtained by saturating a dry substrate with 1 coat (or 2 if required, the 2<sup>nd</sup> applied a few minutes after the 1<sup>st</sup>).
- Drying time : 24 hours (Maximum effectiveness is achieved 5 days after application).
- 235 LANKOPROTEC may revive the sheen of certain substrates (a pre-application test should be carried out).

### PRECAUTIONS

- Temperature range for use : 5°C - 35°C.
- Do not work in direct sunlight or apply to a hot substrate.
- Do not apply during rainfall nor apply to a damp or wet substrate.
- Gloves and eye protection should be worn by persons with sensitive skin.
- In service stations, as the surface is completely protected, it is important to remove any traces of fuel or grease using a suitable absorbent product.

\*The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document.\*

Technical Documentation English-Version Aug 2006

### Davco Construction Materials (Thailand) Co., Ltd.

3rd Floor Lumpini II Building 247 Sarasin Road, Lumpini, Pathumwam, Bangkok 10330 Telephone: 66(0)2651 9027-36 Facsimile: 66(0)2651 8003  
e-mail : thaicustomerservice@davco.co.th, Overseas Offices : Australia (Sydney - Head Office), Singapore

**LANKO**  
**infotech**

[www.lanko.com.au](http://www.lanko.com.au)  
[www.parexlanko.com](http://www.parexlanko.com)

**LANKO**

PAREXGROUP