

LANKO



CHARACTERISTICS

- Suitable for all kinds of mortar.
- Keeps a nice surface.
- Reduces cracking.
- No colour effect.

COVERAGE

50-100 cc. per one 50 kg bag of Portland cement.

PACKAGING

- 5 litre container.

STORAGE

1 year from date of manufacture if stored in unopened original packing in dry, frost-free conditions.

DESCRIPTION

311 LANKOPLAST is a liquid admixture to be mixed with gauging water to control the size and amount of air bubble of the rendering mortar without addition of lime. As a result it will give controlled plasticity and reduce cracking.

The raw materials used in 311LANKOPLAST is specially selected and the quality is in accordance with BS 4887.

USES

- Rendering.
- Brick laying.

SPECIFICATIONS

- Appearance : Clear brown liquid
- Density : 1.005
- Viscosity : 1.5 cps
- pH : 7-8
- Chloride : None

WORK INSTRUCTIONS

Dosage

- 311 LANKOPLAST is added to the gauging water at the rate of 50-100 cc.per one 50 kg bag of Portland cement or 0.1-0.2% of the weight of Portlan cement.

Mixing

- 311 LANKOPLAST must be mixed with clean water as above dosage until obtaining a homogeneous liquid.
- A mixing liquid to be mixed with cement and sand as required ratio.

PRECAUTIONS

- Do not add 311 LANKOPLAST to the mixed mortar.
- 311 LANKOPLAST cannot be used individually without mixing with water.



www.lanko.com.au
www.parexlanko.com

"The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document."

Technical Documentation English-Version Aug 2006

Davco Construction Materials (Thailand) Co., Ltd.

3rd Floor Lumpini II Building 247 Sarasin Road, Lumpini, Pathumwam, Bangkok 10330 Telephone: 66(0)2651 9027-36 Facsimile: 66(0)2651 8003
e-mail : thaicustomerservice@davco.co.th, Overseas Offices : Australia (Sydney - Head Office), Singapore

